LM 17500Primary Li-MnO₂ cell

3 V lithium manganese dioxide A-size spiral cell

Saft's LM 17500 cell is ideally suited for applications requiring high energy and long operating life, with stable voltage under high discharge rates in -40°C / +85°C environment.

Benefits

- High drain/high pulse capability
- High voltage response, stable during most of the lifetime of the application even after long dormant periods
- High capacity at high current and low temperature
- Low self discharge compatible with long operating life (less than 1% after 1 year of storage at +20°C)
- Superior resistance to corrosion
- Low magnetic signature

Key Features

- Spiral construction
- Hermetic construction with glass to metal seal
- Stainless steel container
- Integrated safety vent
- Non corrosive electrolyte
- Non pressurized at room temperature
- Non restricted for transport
- RoHS and REACH compliant
- Made in USA

Designed to meet all major quality, safety and environment standards

- Safety: UL 1642 and IEC 60086-4
- ATEX: Compliant with IEC 60079-11 (T4 rating at +70°C)
- Transport: UN 3090 and UN 3091
- Quality: ISO 9001, Saft World Class Continuous program

Typical Applications

- Utility metering
- Alarms and security
- Tracking systems
- GSM/GPRS communication
- Radio communications systems
- Medical devices



Electrical characteristics	
(Typical values relative to cells stored for one year or less at +.	30°C max)
Nominal capacity (at 30mA +20°C 2.0V cut-off) ¹	3.0 Ah
Open circuit voltage (at +20°C)	3.2 V
Nominal voltage (under 1mA at +20°C)	3.0 V
Nominal energy (at 30mA +20°C 2.0V cut-off)	8.7 Wh
Pulse capability ²	up to 2.0 A
Recommended maximum continuous current	1.5 A
Operating conditions	
Operating temperature range ³	-40°C to +85°0
Storage temperatures	
Recommended	+30°C
Allowable ⁴	-55°C to +90°C
Physical characteristics	
Diameter (max)	17.5 mm
Height (max)	51.5 mm
Typical weight	approx. 28 g
Li metal content	1.0 g max
Termination	
Available termination suffix	
CN, CNR	radial tabs
3 PF, 3 PF RP, 4 PF, 2 PF	radial pins
FL	flying leads
Other configurations upon request	
Dependent upon current drain, temperature and cut-off	

¹Dependent upon current drain, temperature and cut-off.




²Dependent upon pulse characteristics, temperature, cell history and application. Higher rates are available under certain circumstances


³To maintain cell heating within safe limits. Battery packs may imply lower level of maximum current and may require specific thermal protection. Consult Saft.

⁴ Long time storage at high temperature may affect performances. Consult Saft.

LM 17500

LM 17500 dimensions






Storage


 The storage area should be clean, cool (preferably not exceeding +30°C), dry and ventilated.

Warning

- Fire, explosion and burn hazard.
- Do not recharge, short circuit, crush, disassemble, heat above 85°C, incinerate, or expose contents to water.
- Do not solder directly to the cell (use tabbed cell versions instead).



Discharge curves at at 21°C and various discharge currents 3.5 30 mA 3.0 100 mA 450 mA 2.5 1000 mA Voltage 2.0 1500 mA 1.5 1.0 0.5 0.0 0.0 0.5 1.0 1.5 2.0 2.5 3.0 3.5 4.0 **Discharged Capacity (Ah)**





Saft

12, rue Sadi Carnot 93170 Bagnolet France Tel.: +33 (0)1 49 93 19 18 Fax: +33 (0)1 49 93 19 69 www.saftbatteries.com Saft America, Inc. 313 Crescent St.

Valdese, NC 28690 - USA Tel.: +1 (828) 874 4111 Fax: +1 (828) 874 3981

www.saftbatteries.com

Doc N°31125-2-0315 Edition: March 2015 Information in this document is subject to change without notice and becomes contractual only after written confirmation by Saft. Published by the Communications Department Photo credit: Saft